



Specializing in Research & Development of High Performance Pressure Sensitive Tapes

Product Data Sheet

Solvent Based Acrylic Biaxially Oriented Polypropylene Carton Sealing Tape

Product Description: Polypropylene film coated with solvent based acrylic adhesive.

Product	Thickness	Tensile	Elongation	Adhesion	Adhesive Type	Applications
SC-1670 (clear or tan)	2.2 mil	18 lb/in	140%	25 oz/in	Acrylic	Carton Sealing
SC-1680 (clear or tan)	2.6 mil	24 lb/in	150%	29 oz/in	Acrylic	Carton Sealing
SC-1690 (clear or tan)	3.6 mil	36 lb/in	150%	30 oz/in	Acrylic	Carton Sealing
SC-1700 (Clear to Core)	2.2 mil	20 lb/in	140%	27 oz/in	Acrylic	Carton Sealing
SC-1710 (Clear to Core)	2.7 mil	24 lb/in	150%	30 oz/in	Acrylic	Carton Sealing
SC-1720 (Clear to Core)	3.6 mil	36 lb/in	150%	30 oz/in	Acrylic	Carton Sealing

Tape Application

To achieve ultimate bond strength please be sure materials being bonded are clean and free of dust, dirt, oil or other substances which can effect the bond of the tape adhesive. Firm application pressure will promote a strong, long lasting bond. Adhesive bond strength is dependent upon the material type being bonded. If a variety of materials are being used, please be sure to test the suitability of product performance with each material. Please contact Custom Adhesive Products at the phone number below with questions regarding your taping applications and needs.

Notice: Physical and performance values list above are average values obtained from tests performed according to PSTC or ASTM standard test methods. Custom Adhesive Products does not make any warrant of any kind as to the results listed above. The information listed above does not represent a performance guarantee. Product performance may vary with each individual application and the purchaser should test the product prior to use and satisfy themselves regarding product functionality in their application. Custom Adhesive Products shall not be liable for damages in excess of the purchase price of its products or for incidental or consequential damages.